



PALGLAS®

Flat Extruded Acrylic Sheet

PALGLAS offers unsurpassed light transmission, matching that of glass while weighing half. Inherently UV resistant, PALGLAS is the ultimate choice in high traffic acoustic barriers, resisting gasses emitted from vehicles.

PALGLAS has high clarity and formability that opens a world of design options for designers, from small fabricated items to transparent furniture.

Typical Applications

- High traffic acoustic barriers
- Lightweight high clarity glazing
- Attractive fabricated items
- Transparent furniture
- Light fixtures
- Illuminated and 3D signage



10 Years
Warranty



Glass-Like
Appearance



Lightweight



Glossy
Finish




High Optical
Clarity



Clean &
Elegant

Colors



Product Availability

Thickness Standard	2 - 10 mm
Thickness Special	1.5, 1.8, 12 - 30 mm
Width x Length	1250 x 2050 mm
	1220 x 2440 mm
	2050 x 3050 mm

* Other colors and dimensions are available upon request, subject to minimum quantity. Please contact your PALRAM distributor for more information.

Weather and UV Resistance

PALGLAS is inherently resistant to UV radiation. Coupled with its wide service temperature range (-40°C to 80°C), it becomes suitable for outdoor applications. A limited warranty against yellowing is available.

Resistance to Chemicals

PALGLAS is resistant to a wide range of chemicals at room temperature. Detailed information is available upon request.

Forming and Fabrication

PALGLAS can be fabricated, machined and thermoformed. Please note: predrying is strongly recommended for best results when thermoforming. PALGLAS is easily hot line bent and shaped into a wide variety of forms. PALGLAS can be bonded to itself and other materials. Additional details on how to work with PALGLAS is available upon request.

Installation and Maintenance

Large PALGLAS sheets should always be installed using a framing system. PALGLAS thermal expansion is eight times that of glass and three times that of metal, this important factor must be taken into account when glazing. The polyethylene protective masking must be removed immediately after installation. PALGLAS can easily be cleaned with a soft cloth or sponge, using a mild soap or detergent. Rinse and dry with a soft 100% cotton cloth or moist cellulose sponge to prevent water spotting. Ask your Palram representative to assist you in selecting PALGLAS sheet with dimensions that are suitable for your applications.

Acoustic Barrier Related Certification*

Standard	Definition	Classification
EN 1794	Road traffic noise reducing devices: Non-acoustic performances	Compliance
EN 1793	Road traffic noise reducing devices: Acoustic performance	Compliance

* Applies to PALGLAS 15mm & 20mm sheets.

Typical Physical Properties

Property	Method*	Conditions	Units	Value
Density	D-792		g/cm ³	1.19
Heat deflection temperature (H.D.T)	D-648	Load: 1.82 MPa	°C	91
Service Temperature Range			°C	-40 to + 80
Coefficient of linear thermal expansion	D-696		cm/cm°C	7.0 x 10 ⁻⁵
Thermal conductivity	C-177		W/m K	0.19
Tensile strength at break	D-638	1 mm/min	MPa	70
Elongation at break	D-638	10 mm/min	%	4
Tensile modulus of elasticity	D-638	1 mm/min	%	3,200
Flexural strength	D-790	1 mm/min	MPa	110
Flexural modulus	D-790	1 mm/min	MPa	3,200
Izod impact strength notched	D-256	23 °C	J	16
Rockwell hardness	D-785		R Scale	123R
Light transmission	D-1003	Clear sheet	%	92
Haze	D-1003	Clear sheet	%	<1
Yellowness index	D-1003	Clear sheet		<1.5

* ASTM method except where noted otherwise



Transparent Acoustic Barriers



www.palram.com

In as much as Palram Industries has no control over the use to which others may put the material, it does not guarantee that the same results as those described herein will be obtained. Each user of the material should make his own tests to determine the material's suitability for his own particular use. Statements concerning possible or suggested uses of the materials described herein are not to be construed as constituting a license under any Palram Industries patent covering such use or as recommendations for use of such materials in the infringement of any patent. Palram Industries or its distributors cannot be held responsible for any losses incurred through incorrect installation of the material. In accordance with our company policy of continual product development you are advised to check with your local Palram Industries supplier to ensure that you have obtained the most up to date information.

